() CSNRI° ViperSkin™

ViperSkin[™] is the first bi-axial, hybrid carbon and glass fiber, pre-saturated system to blend the unsurpassed strength and stiffness of carbon with the ease and use of a moisture-cured, factorysaturated polyurethane. The pre-saturated system ensures appropriate fiber-to-resin content ratios to deliver reliable performance in restoring pipeline integrity on lines with complex geometry.

APPLICATIONS

- Transmission and distribution pipelines
- Oil and gas risers and subsea structures
- Process piping: chemicals, oil, gases, water, and steam
- Mechanical dents and defects
- Girth welds on vessels and pipelines
- Straight pipelines, elbows, tees, and flanges

COMPLIANT WITH: (standards/certifications)

- AB-539
- ASME PCC-2
- ASME B31
- ISO 24817
- US DOT
- API
- CSA Z662



BENEFITS:

- Factory saturation of moisture-cured polyurethane resin reduces composite field preparation time by more than 50%
- Factory saturation ensures the right fiberto-resin ratio with constant strength and mechanical properties
- Easy application in any conditions, including damp or sweating pipes and in submerged environments
- No heating or post-curing
- Suitable for irregular shapes and geometries
- Can be used on lines of any diameter

ViperSkin™

QUALIFICATION DATA

PROPERTY	CIRCUMFERENTIAL DIRECTION	AXIAL DIRECTION	
Tensile Strength	101.6 ksi (700.6 MPa)	24.9 ksi (172 MPa)	
Tensile Modulus	11.32 Msi (78.05 GPa)	1.75 Msi (12.1 GPa)	
Ply Thickness	0.018" (0.46 mm)		
Hardness	75		
Max Recommended Application Temperature	120°F (50°C)		
Shelf Life	12 months		

CURING SCHEDULE

TEMPERA	TURE	SET TIME	CURE TIME
(C)	(F)	(HRS)	(HRS)
10	50	5.20	24
16	60	3.45	15
24	75	2.30	5.5
32	90	2.00	4.25
49	120	1.00	3

REPAIR SYSTEM COMPONENTS:

- Filler: EPN-101, EPN-242
- Primer: PPR-220, PPR-290
- Prepreg (optional isolation layer): XT-FP
- Prepreg: VS

WARRANTY CSNRI routinely implements product improvements. Please contact your local distributor or office for the most current product specifications. CSNRI warrants the quality of this product when used according to directions.

PS_0923

ISO 9001 Certified

CSNRI°

Sales@cs-nri.com | CSNRIcomposites.com

© 2023 CSC Operating Company, LLC. All Rights Reserved.